

CHEMFLEX POLYURETHANE 100 % SOLID

PRODUCT DESCRIPTION

The CHEMFLEX is a two-component Polyurethane floor coating system. It also possesses superior mechanical and chemical properties best suited for residential and commercial applications as well as a long pot life and working time. The CHEMFLEX has been designed as a waterproofing membrane but is also a top coat PU membrane. The CHEMFLEX formulation is based on a high-performance polymer technology displaying outstanding properties and superior aesthetic finish. We recommend using an appropriate primer for the CHEMFLEX system when used as a waterproofing membrane and applying more than 25 mils when used as an anti-fracturing layer for thick epoxy systems.

USES

The CHEMFLEX provides excellent resistance for the most demanding applications:

- Commercial, residential and industrial uses
- Manufacturing facilities and warehouses
- Commercial centers
- Office buildings
- Retail stores
- Parking garages
- Food/beverage processing and preparation plants
- Public facilities including hospitals and schools
- Pharmaceutical companies

ADVANTAGES

- Environment friendly (100% solids, solvent-free)
- Potential for LEED eligibility
- Odor free
- Easy application with long pot life and working time
- Superior mechanical and chemical properties suited for the toughest applications
- Excellent elongation and abrasion resistance
- Waterproof

APPLICATION DATA

Ratio : 2A :1B
 Format : 3 x gallons
 Color : Grey

Solids Coverage/gal	mils	sq.ft.
	1	1600
	4	400
	8	200
	10	160
	20	80

Shelf life One years in original unopened
 Factory pails under normal storage
 Conditions

Substrate temp. Min 4 °C , max 40°C

Cure time 21 days

TECHNICAL DATA SHEET

Floor Coating: *CHEM FLEX*

Last update: December 2018

Working time	25 min	22°C and 55% rel. hum
Tack free	7 hours	22°C and 55% rel. hum
Hard dry	8 hours	22°C and 55% rel. hum
Light traffic	24 hours	22°C and 55% rel. hum
Normal traffic	1 week	22°C and 55% rel. hum

Solids content 100%

TECHNICAL PROPERTIES

- **Tensile Strength ASTM D 638**
- **Result** >5.8 mpa (>841psi)
- **Tear Resistance ASTM D 624 DIE C**
- **Result** >37 N/mm
- **Adhesion to membrane ASTM D 4541**
- **Result** > 2.5mpa
- **% Elongation ASTM D 638**
- **Résultats** > 350%
- **Adhesion to concrete ASTM D 4541**
- **Result** > 2.5mpa
- **HARDNESS D SHORE ASTM D 2240**
- **Result** > 45±5
- **VOC** ASTM D 2396 0.5 g/l

SURFACE PREPARATION

Concrete should be clean, dry and free of grease, oil, paint, curing agents or any contaminants that may inhibit proper adhesion. Concrete should be cured at least 28 days before applying the coating system. Proper testing procedures should be practiced with regards to soil acidity and moisture vapor transmission. Take a pH reading to ensure concrete is neutral (a reading between 5 and 9 is acceptable). Use a calcium chloride test to measure moisture vapor transmission. Readings of 3.5 lbs/1000 sq. ft. during a

24-hour period or less are acceptable for applying coatings. Higher results should receive a moisture mitigation system. Surface must be prepared mechanically in line with CSP-3-4. Ensure the surface is free of contaminants, and the pores are open to allow the product to penetrate. If the product is applied over an existing epoxy flooring system that has been cured for a period longer than one day it should be sanded with a proper floor machine. A mechanical bond to a sanded surface is required and the pores of the existing coating must be opened for better adhesion. Vacuum dust and properly wipe the surface prior applying CHEM100 PREMIUM. Conduct adhesion tests if there is a doubt about surface preparation. When using a broadcast decorative system, the primer or intermediary coat with the flakes should be sanded and cleaned after appropriate hardness is reached prior applying the top coat. Contact us for more details on how to use the product with broadcast systems.

MIXING

Before final mixing, pre-mix parts A and B individually at low speed. Special attention must be paid to colored versions of the product since pigments may have separated from the rest of the formulation during storage. Mixing should be done until the color is uniform. Then, mix two parts of A and one part of B together at low speed in a separate container. The mixing container must be clean and free of any outside particle. Mix thoroughly for three minutes using a low speed drill (300-450 rpm) to minimize the entrapping of air. Make sure to scrap sides and bottom of mixing container so no unmixed material remains. Mix only the necessary quantity to be used according to the specified pot life / working time.

APPLICATION

Apply only when air and floor temperature is between 4-40°C and the relative humidity less than 85%. The product has been especially designed to

TECHNICAL DATA SHEET

Floor Coating: *CHEM FLEX*

Last update: December 2018

adhere on concrete surfaces. Once the surface has been properly prepared, squeegee and roll back apply the product. It is recommended to apply the product in a multi-directional (north-south, east-west) motion to ensure proper coating thickness. We recommend the application of one base coat and one top coat for total system thickness of approximately 8 to 20 mils. CHEMFLEX will seal the slabs and display higher flexibility hence absorbing potential slabs movements.

Follow the solvent manufacturer instructions for use and warnings.

RECOAT

Do not recoat without sanding if last coating of the product has been applied for more than one day. The floor surface should be sanded/abraded until a uniform dullness is achieved. There should be no gloss on the prior coating after vacuuming and before applying the next coat.

CLEAN UP

Cured product may be disposed of without restriction. Excess liquid A and B material should be mixed together and allowed to cure, then disposed of in the normal manner. Product may be disposed in accordance with provincial and federal regulations. Uncured material can be removed with proper solvent.

LIMITATIONS

Requires a dry substrate. This product should not be applied to concrete substrates that show high levels of moisture/humidity. Although this product may be applied in a wide range of thickness, limitations may apply when taking into consideration curing time. Everything else being equal, thicker is the film, quicker is the curing time. Moisture content of the substrate must be <4% prior to application. Not suited for exterior applications. Temperature will also impact curing time. Curing time may extend significantly at very low temperature levels. Keeping the product stored at room temperature will make the application easier and dry times shorter. CHEMTEC COATINGS stands behind the quality of its products. However, CHEMTEC COATINGS cannot guarantee final results since CHEMTEC has no control over surface preparation, operating conditions and application procedures. Clients are solely responsible to test CHEMTEC'S products to determine if they perform as expected. Contact CHEMTEC COATINGS for further information regarding the limitations of this product.

AVAILABLE COLORS

See Standard Color Chart

- Full color customization available
- Contact us for additional details

Refer to the most recent Material Safety Data Sheet prior using this product

CHEMTEC COATINGS
913, rue Michelin, Laval, QC, Canada, H7L 5B6
Phone : 450-629-1717 / 1-844-829-1717